

PIT MASTER

Coconut Shell & Other Biomass Based Nut Shells Charcoal Briquettes (A-240++)



| PRODUCT INFORMATION | | | |
|--|---|-----------------------|----------------|
| Description | MASTER Bio Based BBQ Briquettes | | |
| Shape | Small Oval-shaped | | |
| Dimensions (W x H x D) | ≅ 65 x 52 x 32 mm | | |
| Weight | ≅ 55 gm | | |
| REPORT OF ANALYZE (DRY BASIC) | VALUE | TOLERANCE | METHOD |
| Ash Content | Max. 8 % | +/- 2 % | ASTM D 1762-84 |
| Fixed Carbon | ≥ 80 % | +/- 4 % | By Calculation |
| Moisture | Max. 8 % | +/- 1 % | ASTM D 1762-84 |
| Estimated Burning time* over 180°C (356°F) | 240 min over 180° Celsius | +/- 10 minutes | Force T -180* |
| Inadmissible Additions | 1 % | + 1 % | ISO 7404-3 |
| Calorific Value | Approximate 7400 | | |
| Reference Standard | Cavron Global | | |
| OTHERS | | | |
| Binder | Tapioca Starch | | |
| Certifications and Standards | BSCI, ISO 9001/ ISO 14001, Bra Miljøval, Din Certco Bio-based | | |
| Manufacturing | Indonesia | | |
| SHIPPING AND TRANSPORT CODES | DOCUMENTS AVAILABLE | | |
| HS Code : 44022010 | MSDS (Material Safety Data Sheet) | Self-Heat Test Report | |
| GAS No. : 68647-86-9 | Vanning Certificate | | |
| UN Code : 1361 | COO (Certificate of Origin) | | |

* Force T-180 test is based on 1kg of briquettes, and a start up time on maximum 18 minutes.

| Date: | Date: | Date: | Date: | Date: |
|----------------|-------------------|-----------------|--------------------|-------------------|
| R&D | Quality Assurance | Product Manager | Compliance Manager | COO |
| Vanda Lengkong | Mushaf Al Farizi | Robert Muntu | Bambang Jarot | Søren I. Pedersen |