

PREMIUM

Coconut Shell & Other Biomass Based Nut Shells Charcoal Briquettes (A-190)



PRODUCT INFORMATION			
Description	PREMIUM Bio Based BBQ Briquettes		
Shape	Square Pillow-shaped		
Dimensions (W x H x D)	≈ 46 x 44 x 28 mm		
Weight	≈ 29 gm		
REPORT OF ANALYZE (DRY BASIC)	VALUE	TOLERANCE	METHOD
Ash Content	Max. 25 %	+/- 2 %	ASTM D 1762-84
Fixed Carbon	≥ 55 %	+/- 2 %	By Calculation
Moisture	Max. 8 %	+/- 1 %	ASTM D 1762-84
Estimated Burning time* over 180°C (356°F)	190 min over 180° Celsius	+/- 10 minutes	Force T – 180*
Inadmissible Additions	N/A	+/- 1 %	ISO 7404-3
Calorific Value	Approximate 5400		
Reference Standard	Cavron Global		
OTHERS			
Binder	Tapioca Starch		
Certifications and Standards	BSCI, ISO 9001/ ISO 14001, Bra Miljøval, Din Certco Bio-based		
Manufacturing	Indonesia		
SHIPPING AND TRANSPORT CODES	DOCUMENTS AVAILABLE		
HS Code : 44022010	MSDS (Material Safety Data Sheet)	Self-Heat Test Report	
GAS No. : 68647-86-9	Vanning Certificate		
UN Code : 1361	COO (Certificate of Origin)		

* Force T-180 test is based on 1kg of briquettes, and a start up time on maximum 18 minutes.

Date:	Date:	Date:	Date:	Date:
R&D	Quality Assurance	Product Manager	Compliance Manager	COO
Vanda Lengkong	Mushaf Al Farizi	Robert Muntu	Bambang Jarot	Søren I. Pedersen